



RUBBER CALENDERED SHEET

DESCRIPTION

DUNLOP 29600 Uncured Natural Rubber – (NR) – Calendered Sheet

APPLICATION

Press Cure – M Grade Natural Rubber Sheeting

STANDARD PRODUCTS

13.1m x 1200mm roll packed into standard box for transport and storage. Thickness range is 1mm to 15mm.

TYPICAL PROPERTIES (Based on 3mm sheet press cured 10 mins @ 160°C)

Tensile Strength	(ASTM D412 method A)	MPa	25.0
Elongation @ Break	(ASTM D412 method A)	%	500
Hardness	(ASTM D2240 Scale "A")	(A/1)	64 +/-5
S.G.			1.11
Shelf Life	@ or below 7 ⁰ C	Months	3

<p>CURING METHOD</p> <p>(Allow additional time for substrate).</p>	<p>Autoclave Cure.</p> <p>a) 6mm 10mins @ 150°C b) 12mm 20mins @ 150°C c) 25mm 60mins @ 140°C</p>
---	---

<p>COMMENTS</p>	<p>1. For specific chemical resistance contact Fenner Dunlop.</p>
------------------------	---

This brochure does not purport to contain all the information that may be required to evaluate this Calendered Sheeting and customers should make their own independent assessment of that product and the data contained in this brochure. Fenner Dunlop does not make any representation or warranty, express or implied, as to the accuracy or completeness of the information contained in this brochure and nothing in this brochure shall be relied upon as a promise or representation, whether as to the past or the future.